



EGC Enterprises, Inc.

140 Parker Court
Chardon, Ohio 44024
Phone: (440) 285-5835

PRODUCT DATA SHEET

PDS-100

TITLE: Thermafoil Ni-K (#) (For any nominal density ex: Ni-K90, Ni-K70...)

INFORMATION ON THIS PRODUCT DATA SHEET IS TYPICAL, SUBJECT TO CHANGE WITHOUT NOTICE AND DOES NOT CONSTITUTE A SPECIFICATION OR PRODUCT WARRANTY.

Description: Thermafoil® NI-K flexible graphite is an uncured laminate made with TF-K flexible graphite sheets at a nominal 90 #/ft² density, adhesively bonded to both sides of a .003" thick fully annealed Nickel 200/201 foil insert.

Thermafoil® NI-K Laminates require a heat activation process to cure the adhesive on laminates 26" x 26" or smaller.

Thermafoil® NI-K Laminates larger than 26" x 60" are constructed without the application of heat using pressure sensitive adhesive.

Jennifer Klum
Department Manager Approval

3/20/13
Date